



RM 1801-02, 1808 & RM 2010,
TOWER B, REGENT CENTRE,
63 WO YI HOP ROAD, KWAI CHUNG,
NEW TERRITORIES, HONG KONG
TEL: (852) 2429 7022 FAX: (852) 2429 7266
ctcasia@ctcgroupe.com

TEST REPORT

Report No.: 03893-14



May 26, 2014

Page 1/3

APPLICANT:
KE GLOTECH LTD.,

198-1, MACHUN-DONG, SONGPA-KU, SEOUL, 138-821, REPUBLIC OF KOREA

Test(s) requested :	EN388 TESTS	Product Category :	--	Product Type :	--
Sample description: ---					
Style / Article no.	: 2135	Buyer	:	--	
Ref no.	: --	Exported to	:	--	
Order no.	: --	Date of receipt of application form	:	May 22, 2014	
Supplier	: --	Date of receipt of sample	:	May 22, 2014	
Number of sample(s)	: 4 PAIRS OF GLOVES	Testing period	:	May 22, 2014- May 26, 2014	
		Service required	:	REGULAR	

1. Conclusion:

Testing	Result	Combine / Separate Test Item(s)	Failed Test Item(s)
Abrasion resistance of glove	Level 1	(S01)	---
Blade cut resistance of glove	Level 2	(S02)	---
Tear resistance of glove	Level 4	(S01)	---

The abrasion resistance got level 1; the blade cut resistance got level 2; the tear resistance got level 4 according to EN 388 standard.

Approved by

Original signed

John Cheung Fai Cheong
Assistant Laboratory Supervisor



RM 1801-02, 1808 & RM 2010,
TOWER B, REGENT CENTRE,
63 WO YI HOP ROAD, KWAI CHUNG,
NEW TERRITORIES, HONG KONG
TEL: (852) 2429 7022 FAX: (852) 2429 7266
ctcasia@ctcgroupe.com

TEST REPORT

Report No.: 03893-14



May 26, 2014

Page 2/3

APPLICANT:
KE GLOTECH LTD.,

2. Label(s) on the sample(s):

Sample(s)	ID	Size	Style/Art. No.	Sub-sample(s)	Component(s)	Colour
(01)	i	--	2135	(a)	Glove	Yellow
(01)	ii	--	2135	(a)	Glove	Yellow
(01)	iii	--	2135	(a)	Glove	Yellow
(01)	iv	--	2135	(a)	Glove	Yellow

Remarks: (1) ID is used for identification in which the numbers of sample received are of the same article, ref. no., colour, etc.

3. Sample(s) description assigned by laboratory:

Test item	Sample(s)	Combine / Separate sub-sample(s)
(S01)	(01)-i+ii	(a)
(S02)	(02)-iii	(a)





TEST REPORT



RM 1801-02, 1808 & RM 2010,
TOWER B, REGENT CENTRE,
63 WO YI HOP ROAD, KWAI CHUNG,
NEW TERRITORIES, HONG KONG
TEL: (852) 2429 7022 FAX: (852) 2429 7266
ctcasia@ctcgroupe.com

Report No.: 03893-14

May 26, 2014

Page 3/3

APPLICANT:
KE GLOTECH LTD.,

4. Test Results :

TEST METHOD		Test item(s) (S01)	Requirement	P/F
1	Abrasion resistance of glove[#] (NF EN 388:2004 §6.1) Lowest value of four tests : Performance Level :	250 1		
2	Tear resistance of glove[#] (NF EN 388:2004 §6.3) Lowest value of four tests (N): Performance Level :	>75 4	---	---

TEST METHOD		Test item(s) (S02)		Requirement	P/F		
3	Blade cut resistance of glove[#] (NF EN 388:2004 §6.2) Sequence 1 2 3 4 5 Average (I): Lowest average value (I) : Performance Level :	Index (I)					
		Test 1					
		3.6		4.2			
		3.9		3.3			
		3.2		3.4			
		4.1		4.0			
		4.0		3.4			
		3.8		3.7			
				3.7			
				2			

Table of Performance Level for Glove

Test Item	Performance Level					
	0 ^{##}	1	2	3	4	5
Abrasion Resistance (NF EN 388:2004 §6.1) Number of cycles (minimum)	< 100	100	500	2000	8000	---
Blade Cut Resistance (NF EN 388:2004 §6.2) Index (I) (minimum)	< 1.2	1.2	2.5	5.0	10.0	20.0
Tear Resistance (NF EN 388:2004 §6.3) Force (N) (minimum)	< 10	10	25	50	75	---

Performance level 0 means the glove falls below the minimum performance level for the given individual hazard.

- End of report -