



RM 1801-02, 1808 & RM 2010,
TOWER B, REGENT CENTRE,
63 WO YI HOP ROAD, KWAI CHUNG,
NEW TERRITORIES, HONG KONG
TEL: (852) 2429 7022 FAX: (852) 2429 7266
ctcasia@ctcgroupe.com

TEST REPORT

Report No.: 03896-14



May 24, 2014

Page 1/3

APPLICANT:
KE GLOTECH LTD.,

MR. HARRY PARK
198-1, MACHUN-DONG, SONGPA-KU, SEOUL, 138-
821, REPUBLIC OF KOREA

Test(s) requested : EN 407 TEST
Sample description: ---
Style / Article no. : KD25
Ref no. : --
Order no. : --
Product Category : --
Product Type : --
Buyer : --
Exported to : --
Date of receipt of application form : May 22, 2014
Date of receipt of sample : May 22, 2014
Testing period : May 22, 2014- May 27, 2014
Supplier : --
Service required : REGULAR
Number of sample(s) : 4 PAIRS OF GLOVES

1. Conclusion:

Testing	Result	Combine / Separate Test Item(s)	Failed Test Item(s)
Contact heat	Level 2	(S01)	---

Note: P: Pass F: Fail

The contact heat got level 2 according to EN 407 standard.

Approved by

Original signed

John Cheung Fai Cheong
Assistant Laboratory Supervisor



TEST REPORT



RM 1801-02, 1808 & RM 2010,
TOWER B, REGENT CENTRE,
63 WO YI HOP ROAD, KWAI CHUNG,
NEW TERRITORIES, HONG KONG
TEL: (852) 2429 7022 FAX: (852) 2429 7266
ctcasia@ctcgroupe.com

Report No.: 03896-14

May 24, 2014

Page 2/3

APPLICANT:
KE GLOTECH LTD.,

2. Label(s) on the sample(s):

Sample(s)	ID	Size	Ref No.	Sub-sample(s)	Component(s)	Colour
(01)	i	--	KD25	(a)	Palm	Yellow
(01)	ii	--	KD25	(a)	Palm	Yellow

Remarks: (1) ID is used for identification in which the numbers of sample received are of the same article, ref. no., colour, etc.

3. Sample(s) description assigned by laboratory:

Test item	Sample(s)	Combine / Separate sub-sample(s)
(S01)	(01)-i+ii	(a)





TEST REPORT



RM 1801-02, 1808 & RM 2010,
TOWER B, REGENT CENTRE,
63 WO YI HOP ROAD, KWAI CHUNG,
NEW TERRITORIES, HONG KONG
TEL: (852) 2429 7022 FAX: (852) 2429 7266
ctcasia@ctcgroupe.com

Report No.: 03896-14

May 24, 2014

Page 3/3

APPLICANT:
KE GLOTECH LTD.,

4. Test Results:

TEST METHOD			Test item(s)					Requirement	P/F	
			(S01)							
1	Contact heat (EN 407:2004 §5.2)							---		
	Contact temperature (°C)		100	250	350	500	Melting Innermost Layer			
	Trial	1	57.7	17.1	11.4	---	No			---
		2	61.3	18.0	12.2	---	No			---
		3	63.3	18.5	11.3	---	No			---
		Mean	60.8	17.9	11.6	---	---			---
	Threshold time (t _i)		61	18	12	---	---			---
	Performance Level :		2							---

Performance level in accordance with EN 407 §5.2

Performance level	Contact temperature (°C)	Threshold time (s)
1	100	≥15
2	250	≥15
3	350	≥15
4	500	≥15

Note: P: Pass F: Fail

- End of report -