



**Asia**

16/F, 17/F & Room 2601-10 & 21,  
TOWER B, REGENT CENTRE,  
63 WO YI HOP ROAD, KWAI CHUNG,  
NEW TERRITORIES, HONG KONG  
TEL: (852) 2429 7022 FAX: (852) 2429 7266  
ctcasia@ctcgroupe.com

## TEST REPORT

**Report No.:** 03456-05



HOKLAS 156

**November 23, 2005**

**Page 1/3**

**APPLICANT:**  
**KE GLOTECH LTD.,**

SANDY SEO  
198-1 MACHUN-DONG, SONG PA-KU, SEOUL,  
KOREA.

**Test(s) requested :** EN388 TEST **Product Category :** -- **Product Type :** --

**Sample description:** KEVLAR KNITTED HOT MILL GLOVE, OUT LAYER : 100% KEVLAR, INNER LAYER: LINING COTTON AND POLYESTER

**Style / Article no.** : 2505 D-28  
**Ref no.** : --  
**Order no.** : --

**Buyer** : --  
**Exported to** : --  
**Date of receipt of application form** : Nov 12, 2005  
**Date of receipt of sample** : Nov 12, 2005  
**Testing period** : November 12, 2005-  
November 21, 2005  
**Service required** : REGULAR

**Supplier** : --

**Number of sample(s)** : 4 PAIRS OF SAMPLE

### 1. Conclusion:

Testing	Result	Combine / Separate Test Item(s)	Failed Test Item(s)
Abrasion resistance of glove	Level 1	(S01)	---
Tear resistance of glove	Level 4	(S01)	---
Blade cut resistance of glove	Level 5	(S02)	---

Note: P: Pass F: Fail

The abrasion resistance of glove got level 1; the tear resistance got level 4 and blade cut resistance got level 5 according to NF EN 388 standard.

Approved by

Original signed

John Cheung Fai Cheong  
Assistant Laboratory Supervisor

The report is issued by CTC Asia Ltd. under its General Conditions printed overleaf. The Results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Asia Ltd. for more than 6 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory. Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS directory of accredited laboratories. The results shown in this report were determined by this laboratory in accordance with its terms of accreditation.