

Z669

FKM 90 black ED LT45

Rev. 03

General Application

Temperature Range

From -45°C
To +220°C

General Environmental

Application

Chemicals
Hydrocarbons
Low Temp.
CO2 contact

Curing System

Peroxide

Compliances

Norsok M710

Note

*compressione 50%

Disclaimer

Tests performed on test slabs. Temperatures, applications, and indications are meant as basic suggestions and valid for static applications with no other specific media and or conditions.

PHYSICAL AND MECHANICAL PROPRIETIES

Property	Test STD	Unit	Value
Density	ASTM D297	g/cm ³	1.83 ± 0.03
Hardness	ASTM D2240	Shore A	90 ± 5
Tensile Strength	ASTM D412	MPa	>15
Elongation	ASTM D412	%	>115

LOW TEMPERATURE RESISTANCE

Property	Test STD	Unit	Value
TR10	ASTM D1329	°C	<-40

COMPRESSION SET TESTS

Parameters	TEST STD	Unit	Value
24h @ 150°C*	ISO 815	%	<28
72h @ 200°C	ASTM D395 B	%	<33

AGEING PROPERTIES

Heat Aging – 94h @ 200°C Standard: ASTM D573

Properties	Unit	Value
Hardness	Shore A	+4.0
Tensile Strength	%	-10.0
Elongation	%	-15.0
Volume	%	
Weigth	%	

IRM OIL 903 – 70h @ 150°C Standard: ASTM D471

Properties	Unit	Value
Hardness	Shore A	-2.0
Tensile Strength	%	-8.5
Elongation	%	+1.5
Volume	%	+2.0
Weigth	%	

FAM B – 168h @ 23°C Standard: ASTM D471

Properties	Unit	Value
Hardness	Shore A	-11.0
Tensile Strength	%	-23.0
Elongation	%	-15.0
Volume	%	+16.0
Weigth	%	

Standard:		
Properties	Unit	Value
Hardness	Shore A	
Tensile Strength	%	
Elongation	%	
Volume	%	
Weigth	%	

